

---

# FIBER GASKET SETS

---

Durlon® 9000 has been proven through the “Test Protocol” of the Chlorine Institute and is listed as an acceptable gasket material for dry chlorine service (both liquid and gaseous) in Pamphlet 95, Ed.3 of the Chlorine Institute.



## AFGS

### Chlorine Institute Emergency Kit-A Fiber Gasket Set includes:

- (5) 2B Gasket, 15/16" Dia. x 1/16" Durlon® 9000
- (5) 2BB Gasket, 1" x 3" x 1/16" Rec. Durlon® 9000
- (5) A-5 Vent Valve Packing, Garlock
- (5) A-12 Washer, 15/16" O.D. x 9/16" I.D. x 1/16", Durlon® 9000
- (1) A-13 Plastic Box



## BFGS

### Chlorine Institute Emergency Kit-B Fiber Gasket Set includes:

- (3) 4D 1-1/4" OD x 11/16" ID x 1/16" Durlon® 9000
- (5) 4G Gasket, 15/16" Dia. x 1/16" Durlon® 9000
- (5) 4GG Gasket, 1" x 3" x 1/16" Rec. Durlon® 9000
- (5) B-4 Vent Valve Packing, Garlock
- (5) B-11 Washer, 15/16" O.D. x 9/16" I.D. x 1/16", Durlon® 9000
- (1) B-12 Plastic Box

## Durlon® 9000

Pure PTFE resins homogeneously blended with various inorganic fillers.

### Physical and mechanical properties:

- Color - Blue
- Filler- Inorganic
- Temperature Range: -350° to 520°F (-212° to 271°C)
- Pressure Max: 1500 psig (103bar)
- Density: 2.2 g/cm<sup>3</sup> (138lbs./ft.<sup>3</sup>)
- Tensile Strength: ASTM F152: 2,000psi (13.8MPa)
- Compressibility, ASTM F36: 8 to 16%
- Recovery: ASTM F36: 40%

**SHELF-LIFE:** Gaskets have a recommended 10 year shelf-life or after each use.

---

# INDIANSPRINGS

Indian Springs Manufacturing Co., Inc. PO Box 469 Baldwinsville NY 13027-0469. (315) 635-6101  
www.indiansprings.com